



Mary-Ann Warmerdam
Director

MEMORANDUM

Edmund G. Brown Jr.
Governor

TO: Randy Segawa
Environmental Program Manager I
Environmental Monitoring Branch

FROM: Bruce Johnson, Ph.D.
Research Scientist III
Environmental Monitoring Branch
916-324-4106

DATE: March 4, 2011

SUBJECT: STUDY REQUIREMENTS FOR FILM PERMEABILITY MEASUREMENTS

Minimum requirements for film permeability study:

1. Test method and test conditions

- a. General descriptions provided in Papiernik et al. (2001, 2002, 2010). A more detailed methodology presented in Qian et al. (undated).
- b. Temperatures 20-25 C
- c. Two humidity conditions
 - i. Source cell humidity < 45%, receiver cell humidity < 45%
 - ii. Source cell humidity > 90%, receiver cell humidity <45%
 1. Papiernik et al. (2010) describes humidity modifications
- d. Study duration
 - i. Until reaching one of the following
 1. 7 days
 2. Cr/Cs=0.95
- e. Sampling frequency
 - i. Structured to sample more intensively at the beginning where the fastest concentration change will occur
- f. Three replicates per humidity condition
 - i. A single film will require six determinations
 - ii. Replications in three physically different cells
- g. Analysis using "Film Permeability Analysis" FilmPC as provided by SR Yates



2. Reporting requirements

- a. Cell dimensions and location of ports
- b. Spiking procedure – enough information to calculate the initial concentration
- c. Initial concentrations (actual concentrations as mass/volume)
 - i. Measured initial concentration
 - ii. Theoretical initial concentration (based on spiking procedure)
- d. Method of gas analysis
- e. Detection limit for analysis
- f. Measured time course of concentrations in source and receiving chambers
- g. Results of analysis using PC FILM software
 - i. Plot of measured values vs model solution
 - ii. Estimates for h (mass transfer coefficient),
- h. Conditions
 - i. Laboratory temperature
 - ii. Laboratory humidity
 - iii. Source cell humidity
 1. describe how determined
- i. Tarp information
 - i. Name
 - ii. Manufacturer
 - iii. Thickness
 - iv. Color
 - v. Color digital photographs of film identification label
 - vi. Is film embossed
- j. Sample instrument linearity determinations
 - i. Frequency of linearity determinations in relation to samples

Randy Segawa
March 10, 2011
Page 3

REFERENCES

Papiernik, Sharon K., S.R. Yates and Jianying Gan. 2001. An approach for estimating the permeability of agricultural films. *Environmental Science and Technology* 35(6):1240-1246.

Papiernik, S.K., F.F. Ernst, and S.R. Yates. 2002. An apparatus for measuring the gas permeability of films. *J. Environ. Qual.* 31:358-361.

Papiernik, Sharon K., Scott R. Yates and Daniel O. Chellemi. (In press). A standardized approach for estimating the permeability of plastic films to soil fumigants under various field and environmental conditions. *JEQ* Volume 39. Published online 13 Sept 2010.

Qian, Yaorang, Alaa Kamel, Chuck Stafford, Thuy Nguyen and Scott Yates. (undated) *Film Permeability Determination Using Static Permeability Cells*